



www.fusiondigitalpaper.com

7.5 mil fusion soft polyester

DESCRIPTION: High Heat Toner Printable Polyester Synthetic

SPECIFICATIONS:

Total Weight:	6.25 ± 0.20 oz./sq. yd (210 gsm)
Thickness:	0.0074 ± 0.0010 in.
Opacity:	>98%
Brightness:	94
Sheffield Smoothness:	155
Parker Print Smoothness:	5.9
Elmendorf Tear (MD):	315 grams
Elmendorf Tear (CD):	330 grams
Break/Elongation (MD):	51 lbs/in, 62%
Break/Elongation (CD):	48.5 lbs/in, 63%
Stiffness, Taber Units:	
Short Direction -	30
Long Direction -	29
Surface Resistivity (ANSI IEC 60093):	11
COF Static:	0.741 grams-force
COF Kinetic:	0.720 grams-force

Style FL530W

ALL VALUES SHOWN ARE AVERAGE VALUES OBTAINED FROM COMMERCIAL PRODUCTION. THEY ARE INTENDED AS A GUIDE TO PRODUCT PROPERTIES AND NOT TO BE REGARDED AS SHIPPING SPECIFICATIONS.