



www.fusiondigitalpaper.com

fusion extreme permanent

DESCRIPTION: Woven Polyester, Laser Printable, with 1.2 mil cold temp solvent acrylic PSA

SPECIFICATIONS:

Base Denier: 70
Total Weight: 237 gsm
Facestock Thickness: 0.0032 mil \pm 0.0005 mil
Adhesive Thickness: 0.0012 in
Total Thickness: 0.0089 in
(w/ 78lb Clay Coat liner)
Stiffness MD: 12 \pm 2 mg
CD: 9 \pm 2 mg
Opacity: 93% minimum
Tear Strength MD: 310 \pm 50 gm
CD: 322 \pm 50 gm

GENERAL: Urethane coated polyester fabric laminated to a 1.2 mil solvent acrylic adhesive. The fabric facestock is dimensionally stable, highly conformable, and durable to long term environmental exposure. The product is resistant to alcohol, selected solvents, detergents, alkali and acidic reagents. The printed surface is extra smooth for premium printing requirements, including thermal transfer and dry toner laser.

This product has been demonstrated to meet requirements for certain cryogenic labeling specifications.

RECOMMENDED PRINTING METHOD: Thermal transfer, laser, offset, flexography, and hotstamp.

Style PS653WPSA

ALL VALUES SHOWN ARE AVERAGE VALUES OBTAINED FROM COMMERCIAL PRODUCTION. THEY ARE INTENDED AS A GUIDE TO PRODUCT PROPERTIES AND NOT TO BE REGARDED AS SHIPPING SPECIFICATIONS.